




**Part Number:** EFS-0653327-026





Revision: 2023-Dec-06



<b>A</b>	65.1 ± 0.97 mm	2.563 ± 0.038 in
<b>B</b>	32.5 ± 0.48 mm	1.280 ± 0.019 in
<b>C</b>	27 ± 0.53 mm	1.063 ± 0.021 in
<b>D</b>	22.2 mm (min.)	0.874 in (min.)
<b>E</b>	44.2 mm (min.)	1.740 in (min.)
<b>F</b>	19.7 ± 0.41 mm	0.776 ± 0.016 in

<b>Mass</b>	(approximate)	230 grams/half
<b>Magnetic Dimensions</b>	A <sub>e</sub> - Eff. Mag. Cross Section	5.40 cm <sup>2</sup>
	L <sub>e</sub> - Eff. Mag. Path Length	14.7 cm
	V <sub>e</sub> - Eff. Core Volume	79.4 cm <sup>3</sup>
	WA - Min. Eff. Window Area	5.35 cm <sup>2</sup>
	sa - Surface Area	177 cm <sup>2</sup>
<b>Inductance</b>	μ <sub>i</sub> (reference)	26
	A <sub>L</sub> value (nominal)	162 nH/N <sup>2</sup>
	Test Winding	N=100, #16 AWG
	Frequency	10 kHz
	Voltage on Agilent 4284A	2.4 V
A <sub>L</sub> tolerance	±8%	
<b>Core Loss</b>	$\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}} + d \cdot B_{pk}^2 \cdot f^2$	
	where B <sub>pk</sub> expressed in gauss, f expressed in hertz, and:	
	a=1.000E+06, b=1.699E+08, c=3.117E+06, d=6.335E-14	
	B <sub>pk</sub>	300 G
	frequency	100 k Hz
<b>DC Saturation</b>	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$	
	where H expressed in oersteds, and:	
	a=1.000E-02, b=9.592E-07, c=1.553, d=0.000	
<b>Coating/Pkg</b>	H <sub>bc</sub>	200 Oe
	Percent Initial Perm.(nom.)	73.5 %
	Percent Initial Perm.(min.)	67.7 %
	Coating Type:	None
<b>Winding Table</b>	Voltage Breakdown (min.)	N/A
	Limit	N/A
	Package Quantity	42 Halves/Box

<b>Wire Size</b>	AWG	8	10	12	14	16	18	20	22	24	26	28
	mm	3.150	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315
<b>Full Winding</b>	Turns	29	45	69	107	165	256	396	614	950	1,470	2,275
	Rdc(Ω)	8.5 m	21.0 m	51.1 m	126.0 m	309.1 m	762.6 m	1.9	4.6	11.4	28.0	69.0



**Handling and Storage:** Cores should be stored in the original unopened packaging between -10°C and +50°C and less than 60% relative humidity. After the original packaging is opened, the cores should be stored between -8°C and +25°C less than 30% relative humidity. Gloves should be used when handling uncoated cores. The cores should also be sheltered from rain, moisture, salt water, salt air, plasters, ashes, sulfur, sulfur dioxide, ammonia sulfates, soils, acids, metals shavings, and solvents.

**Operating Temperature:** Cores can be used continuously at operating temperatures between -60°C and +200°C.

RoHS 2.0, REACH and ISO (TS16949, ISO 9001, ISO 14001) compliant. Statements available for download at [www.micrometals.com](http://www.micrometals.com).  
 Micrometals Alloy Powder Cores, A Division of Micrometals, Inc. - 5615 E. La Palma Ave., Anaheim, California 92807 USA  
 Ph: +1-714-970-9400, Toll Free in USA: +1-800-356-5977, Asia Pacific Sales: +852 3106 3736