MICROMETALS™
POWDER CORE SOLUTIONS

Part Number:	FS-250090-2

Revision 2021-Dec-01 - Generated 2021-Dec-01



(If coated, Max./Min. includes coating)

OD	(nom. - bare core)	63.50 mm	2.500 in
	(max.)	64.77 mm	2.550 in
ID	(nom. - bare core)	31.37 mm	1.235 in
	(min.)	30.48 mm	1.200 in
HT	(nom. - bare core)	25.00 mm	0.984 in
	(max.)	25.90 mm	1.020 in
Mass	(approximate)	380 grams	
Magnetic Dimensions	A_e - Eff. Mag. Cross Section	3.89 cm²	
	L_e - Eff. Mag. Path Length	14.314 cm	
	V_e - Eff. Core Volume	55.8 cm³	
	WA - Min. Eff. Window Area	7.30 cm²	
	sa - Surface Area	150 cm²	
	mlt - mean length per turn	10.1 cm	
Inductance	μ_i(reference)	90	
	A_L value (nominal)	310 nH/N²	
	Test Winding	N=100, #18 AWG	
	Frequency	10 kHz	
	Voltage on Agilent 4284A	1.7 V	
	AL tolerance	±8%	
Core Loss	Core Loss(mW/cm³)= $\frac{f}{\frac{a}{Bpk^3}+\frac{b}{Bpk^{2.3}}+\frac{c}{Bpk^{1.65}}}+d\cdot Bpk^2\cdot f^2$		
	where B_{pk} expressed in gauss, f expressed in hertz, and:		
	a=4.222E+08, b=6.073E+08, c=2.905E+06, d=4.589E-14		
	B_{pk}	1000 G	
	frequency	50 kHz	
	Core Loss (nominal)	571 mW/cm³	
	Core Loss (maximum)	657 mW/cm³	
DC Saturation	$\%\mu_i \frac{1}{a+b\cdot H^c}+d$		
	where H expressed in oersteds, and:		
	a=1.000E-02, b=9.719E-07, c=1.995, d=0.000		
	H_{DC}	50 Oe	
	Percent Initial Perm(nom.)	80.7%	
	Percent Initial Perm(min.)	74.4%	
Coating/Pkg	Coating Type:	Blue Epoxy	
	Voltage Breakdown (min.)	1000 Vrms	
	Limit	0.1 mA, 5 s	
	Package Quantity	27 Pcs/Box	









Winding Table	**Wire Size**	AWG	8	10	12	14	16	18	20	22	24	26	28
		mm	3.150	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315
	Single Layer	Turns	23	29	37	47	59	74	93	116	145	182	227
		Rdc(Ω)	4.8 m	9.6 m	19.5 m	39.4 m	78.6 m	156.9 m	313.5 m	622.0 m	1.2	2.5	4.9
	Full Winding	Turns	38	59	91	142	219	339	525	813	1,258	1,947	3,013
		Rdc(Ω)	7.9 m	19.6 m	48.0 m	119.0 m	291.9 m	718.6 m	1.8	4.4	10.7	26.4	65.0